

**Con-Tour-MST  
(Micro Spray Texture)**

is a high density, cement mixture specifically engineered for resurfacing and/or texturing exterior and interior concrete. MST is a one component polymer modified Portland cement based formulation. MST bonds chemically and achieves in excess of 7000 PSI compressive strength. MST can be purchased white or colors can be used to create knock down or full coverage designs, then cured, sealed, or stained.

**Surface Preparation**

Surfaces must be structurally sound and completely clean. Remove all bond breakers, dirt, oils or any contaminants using Crete-Clean and Crete-Strip. Also clean surfaces using a 3000 PSI high-pressure power washing or abrasive blast. Clean out debris from expansion joints and tape or mask off the joints to prevent the material from filling the expansion joint. All cracks should be repaired prior to application. Patch damaged areas using Rapid Set 10 Repair Mortar. Apply Surface Prep where concrete is deteriorated or dusty.

**Mixing and Application**

Mix 4.5 to 5 quarts of water for each 50 lb bag. Mix for three to five minutes in a pail with an electric drill and paddle blade. Allow material to sit for three to five minutes, then re-temper with water and mix for two additional minutes.

**Limitations**

Although repairing cracks in the substrate is always recommended prior to installing MST, we cannot warrant that cracks will not re-appear. Do not use this product if the air or substrate temperature is below 50 F. DO NOT USE this product if rain or freezing temperatures are expected within 24 hours.



**Hopper Gun Application**

Spray the MST mixture onto the area achieving desired coverage. Be sure to maintain a damp edge when overlapping to help minimize natural color and texture variation between areas. MST sets firmly in about 10-15 minutes. MST can be sprayed in multiple layers, in various colors, to achieve unlimited Artisan designs. MST can be applied from 1/16” thick and up for texture and up to 1/4” when hard troweling.

**General Application**

Con-Tour MST can be used for many applications where minimal thickness is needed. It can be troweled smooth and/or textured to achieve various effects. In some cases, it can be sprayed onto vertical substrates to achieve many different textures.

**General Information**

The pot life of MST is approximately 30 minutes at 70°F and will vary with the ambient temperature. In warm weather use cold water to extend the working time. Discard any material that begins to set in the bucket. Con-Tint color hardener and release can be used in custom design tinting applications. Marble-Tone stains and Con-Seal Sealers can be applied after final set. Spray Texture is ready for foot traffic after 8 hours, and heavier traffic after 48 hours.

**Coverage**

50 lb bag will cover approximately 50 sq ft at 1/8” (0.3 cm).

**Safety Data**

See Material Safety Data Sheet

